

(19) World Intellectual Property  
Organization  
International Bureau



534230

(43) International Publication Date  
21 May 2004 (21.05.2004)

PCT

(10) International Publication Number  
**WO 2004/041749 A1**

- (51) International Patent Classification<sup>7</sup>: **C04B 41/63**, G01N 33/38
- (21) International Application Number: PCT/AU2003/001472
- (22) International Filing Date: 6 November 2003 (06.11.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 2002301894 7 November 2002 (07.11.2002) AU
- (71) Applicant (*for all designated States except US*): **NAWKAW HOLDINGS B.V.** [NL/US]; C/- Gary L. Coulter, Esq., P.O. Box 662, Athens, GA 30603 (US).
- (72) Inventor; and
- (75) Inventor/Applicant (*for US only*): **WATLING, Anthony, John** [AU/AU]; Unit 2, 369 Alfred Street North, Neutral Bay, New South Wales 2089 (AU).
- (74) Agents: **BORG, Keith, Joseph et al.**; Halford & Co., Level 7, 1 Market Street, Sydney, New South Wales 2000 (AU).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**  
— *with international search report*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: COLOURING MASONRY SURFACES

(57) Abstract: A method of coating a masonry product or structure, in which a single coating of a tinting composition is made on the exposed surface of the masonry product or structure that maintains its look, feel or texture, the masonry product or structure being chosen for suitability by passing one or both of the following tests: A) Wet Area Method: 2 millilitres of water discharged onto the masonry surface within one second at 20-25°C. Will wet out approximately 6 to 34 square centimetres (1 to 5 square inches) of the masonry surface in one minute, or B) Total Absorption Method: 2 millilitres of water discharged onto the masonry surface within one second at 20-25°C. is completely absorbed into the masonry surface within the period of 10 to 60 seconds. The preferred tinting compositions are aqueous latex emulsions.

WO 2004/041749 A1